



Technische Information

Deckschicht	Siehe Produktdatenblatt 01.001
Dämmkern	Formstabile, druckbelastbare Mineralwolle-Dämmplatte Dichte ca. 77 bis 110 kg/m ³
Paneelherstellung	Verklebung
Brandprüfung	Prüfung in Vorbereitung A2 nach DIN 4102 - nicht brennbar
Zulassung	In Zertifizierung gemäß EPD - ISO 14025 sowie DIN EN 15804
Elementbreite	520 bis 1200 mm
Elementdicke	65 mm, 115 mm, 175 mm
Elementlänge	Standard 2500 mm Größere Längen auf Anfrage
U-Wert	0,35 W/m ² K (bei Elementdicke 100 mm)



Produktdatenblatt
02.002
Blatt 1 von 1

The data contained in this publication are based on our current knowledge and experience. They do not constitute the agreed contractual quality of the product and, in view of the many factors that may affect processing and application of our products, do not relieve processors from carrying out their own investigations and tests. The agreed contractual quality of the product at the time of transfer of risk is based solely on the data in the specification data sheet. Any descriptions, drawings, photographs, data, proportions, weights, etc. given in this publication may change without prior information. It is the responsibility of the recipient of our product to ensure that any proprietary rights and existing laws and legislation are observed.

Edition: 01 2014

This data sheet will be rendered invalid if it is superseded by a later version.

C3 Technologies GmbH

Blücherstraße 24
06120 Halle / Saale
Germany

T +49 345 213898-60
F +49 345 213898-69
E info@c3technologies.com
W www.c3technologies.com